

**SECTION 32 17 26.06
SKIDGUARD NON-SKID COATING**

PART 1 - GENERAL

1.01 SUMMARY

- A. Performance-type specification for: On-site, surface-applied non-skid polymer surfacing for the purpose of _____.
 - 1. Materials are not adversely affected by high water tables.

1.02 RELATED REQUIREMENTS

- A. 01 74 19 - Construction Waste Management and Disposal: For additional sustainability requirements of products specified in this Section.
- B. 03 30 00 - Cast-in-Place Concrete: Concrete for sidewalks and platforms.
- C. 09 90 00 - Painting: Includes other products of similar function.
- D. 32 17 23 - Pavement Markings: Includes other products of similar function.

1.03 DEFINITIONS, ABBREVIATIONS, AND ACRONYMS

- A. CSP: Concrete Surface Profile as defined by the International Concrete Repair Institute.
- B. DCoF: Dynamic Coefficient of Friction.

1.04 REFERENCES

- A. ANSI A326.3 Dynamic Coefficient of Friction (DCOF) of Hard Surface Flooring Materials (Laboratory test).
- B. ASTM C482 Standard Test Method for Bond Strength of Ceramic Tile to Portland Cement Paste.
- C. ASTM C501 Standard Test Method for Relative Resistance to Wear of Unglazed Ceramic Tile by the Taber Abraser.
- D. ASTM D570 Standard Test Method for Water Absorption of Plastics.
- E. ASTM D635 Standard Test Method for Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position.
- F. ASTM D638 Standard Test Method for Tensile Properties of Plastics.
- G. ASTM D711 Standard Test Method for No-Pick-Up Time of Pavement Markings.
- H. ASTM D1148 Standard Test Method for Rubber Deterioration—Discoloration from Ultraviolet (UV) or UV/Visible Radiation and Heat Exposure of Light-Colored Surfaces.
- I. ASTM D2196 Standard Test Methods for Rheological Properties of Non-Newtonian Materials by Rotational Viscometer.
- J. ASTM D2205 Standard Guide for Selection of Tests for Traffic Paints.
- K. ASTM D2240 Standard Test Method for Rubber Property—Durometer Hardness.
- L. ASTM D2843 Standard Test Method for Density of Smoke from the Burning or Decomposition of Plastics.
- M. EN ISO 9239-1 Reaction to Fire Tests for Floorings.

- N. EN ISO 11925-2 Reaction to Fire Tests — Ignitability of Products Subjected to Direct Impingement of Flame; Part 2: Single-flame source test.
- O. ASTM G155 Standard Practice for Operating Xenon Arc Lamp Apparatus for Exposure of Materials.

1.05 ADMINISTRATIVE REQUIREMENTS

- A. Preapplication Meeting at Project Site in accordance with 01 30 00 - Administrative Requirements:
 - 1. Convene two weeks prior to start of Work of this Section.
 - 2. Required Attendees: Architect's representative.
 - 3. Review:
 - a. Substrate:
 - 1) Determination of existing concrete surface profile (CSP).
 - 2) Confirm products and processes required for surface preparation of existing substrate.
 - b. Preparation and application procedures to include finalization of personnel and equipment.
 - c. Masking: As required to protect adjacent materials.
 - d. Schedule and coordination required with related work to avoid delays.

1.06 SUBMITTALS

- A. Submittal Procedures: Refer to 01 30 00 - Administrative Requirements.
- B. Product Data:
 - 1. Do not provide manufacturer's Safety Data Sheets.
 - 2. Provide product criteria, characteristics, and current accredited testing data.
 - 3. Provide manufacturer's written application instructions.
- C. Shop Drawings:
 - 1. Provide plan indicating dimensioned product and locations of application from adjacent materials and transitions.
 - 2. Provide locations of joints to remain free of applied product.
- D. Qualification Statements for: Manufacturer and Applicator.
 - 1. Applicator to provide current documentation of training, certification, and authorization by manufacturer.
- E. Manufacturer's Installation Instructions:
 - 1. Provide summary of manufacturer requirements to include special preparation of substrate, application and attachment methods, and conditions requiring special attention.
- F. Warranty Documentation:
 - 1. Provide Executed Warranty.
 - a. Refer to exceptions affecting validation of warranty.
 - 2. Submit warranties listed below, completed in Owner's name and registered with manufacturer.

1.07 MAINTENANCE REQUIREMENTS

- A. For additional requirements refer to 01 60 00 - Product Requirements.
- B. Methods for maintaining materials and finishes.
- C. Precautions about cleaning materials and methods that could be detrimental to components, finishes, and performance.

1.08 SAMPLES AND MOCKUPS

- A. Samples:
 - 1. Verification Sample at Architect's request: Provide minimum 7 inch by 3 inch sample of Non-Skid Coating, indicating manufacturer, product line, and specified color.

1.09 QUALITY ASSURANCE

- A. Refer to 01 40 00 - Quality Requirements for additional requirements.
- B. Source Quality Control: Products and accessories to be by a single manufacturer.
- C. Qualifications:
 - 1. Manufacturer Qualifications: Company specializing in manufacturing products specified in this section, with at least ten (10) years of documented experience with facilities equipped to meet requirements.

1.10 DELIVERY, STORAGE, AND HANDLING

- A. Refer to 01 74 19 - Construction Waste Management and Disposal for packaging waste requirements.
- B. Store in environment meeting a temperature range between 25 degrees F and 90 degrees F.
- C. Remove and replace components at no additional cost to the Owner which are delivered to site damaged or otherwise not suitable for application.

1.11 FIELD CONDITIONS

- A. Environmental Limitations: Successful application of products specified in this Section are dependent on ambient temperature and substrate moisture content requirements within tolerances required by manufacturer.
 - 1. Ratio of Catalyst is determined by ambient temperature.
- B. Inclusion of Reducer is determined by existing substrate condition.

PART 2 - PRODUCTS

2.01 SKIDGUARD NON-SKID COATING COMPONENTS - PERFORMANCE

- A. Products require certified compatibility with concrete mix for a warrantable application of the designed condition.
- B. No substitutions. Products proposed for reselection due to availability to include the following salient features. Refer to Section 01 60 00 - Product Requirements.
- C. Basis of Design: SkidGuard Non-Skid Coating by Vanguard ADA Systems; www.VanguardOnline.com.
 - 1. Source Limitations: Furnish products produced by single manufacturer and obtained from single supplier.
 - 2. Salient Features:
 - a. Coating Thickness at Pavement Surface: As recommended by Applicator while maintaining ADA compliance.
 - b. Width of Non-Skid Coating Application: Per project requirements.
 - c. Location: Based on project requirements.
 - d. Color: LI-B35 [Black] [Yellow] [LumaLine White].
 - 3. Performance Requirements:

- a. Materials to achieve and retain a level of slip-resistance at least meeting those of surrounding pedestrian surfaces.
- b. Wet Surface Friction: Minimum Average 54, in accordance with ASTM E303.
- c. Dynamic Coefficient of Friction (CoF):
 - 1) Greater than or Equal to 0.69: Wet Dynamic CoF as tested in accordance with ANSI A326.3.
- d. Material Properties, non-skid polymer coating:
 - 1) Abrasion Resistance: Average 4.162 gram loss in accordance with ASTM C501.
 - 2) Adhesion (Substrate to be confirmed through submittal of mix design):
 - (a) Asphalt: Dependent on tensile nature of substrate.
 - (b) Portland Cement: 200 PSI, minimum.
 - 3) Bond Strength: Minimum 613 PSI in accordance with ASTM C482.
 - 4) Chemical Resistance: Tested for 7 days.
 - (a) Road Salts: no effect.
 - (b) Anti-freeze: no effect.
 - (c) Diesel fuel: no effect.
 - (d) Gasoline: no effect.
 - (e) Transmission fluid: no effect.
 - (f) Motor oil: no effect.
 - 5) Discoloration from UV and Heat: Average 2.91, in accordance with ASTM D1148.
 - 6) Elongation: 20 percent minimum, in accordance with ASTM D638.
 - 7) Flame Spread: Less than 150 mm, in accordance with EN ISO 11925-2.
 - 8) Hardness: Shore Durometer, A-1, 80 minimum after 24 hours.
 - 9) Rate of Burn: No sustained burn, in accordance with ASTM D635.
 - 10) Smoke Density Rating: Average 0.1, in accordance with ASTM D2843.
 - 11) Smoke Development: Pass, in accordance with EN ISO 9239-1.
 - 12) Shore Hardness: Shore Durometer, A-1, 80 minimum after 24 hours, in accordance with ASTM D2240.
 - 13) Tensile Strength: 125 PSI minimum at break, in accordance with ASTM D638.
 - 14) Tracking: None after 60 minutes max, in accordance with ASTM D711, 50 mils wet at 77 deg F.
 - 15) UV Resistance: 99% minimum Fade Resistance and Color Retention in accordance with ASTM G155.
 - 16) Viscosity: 6000-12000 cps ASTM D2196 - Brookfield #7 spindle at 20 rpm, 77 deg F.
 - 17) VOC: Less than 10 grams per liter maximum, in accordance with ASTM D2205.
 - 18) Water Absorption: Maximum 1.81 percent. Tested in accordance with ASTM D570.
4. Accessories required for application:
 - a. Sand: Added by volume : As determined by Applicator.
 - 1) Silica Sand: 30-60 grain size dry sand.
5. Optional Accessory: SkidGuard LumaLine Liquid Plastic Kit (Glow-In-The-Dark)
 - a. UL1994 Standard Safety Luminous Egress Path Marking Systems: Pass.

PART 3 - EXECUTION

3.01 EXAMINATION AND VERIFICATION

- A. Verify existing conditions meet manufacturer's requirements before starting Work.
 1. Assess CSP existing substrate profile to determine extent of surface preparation required below.
 2. Verify written approval has been received for material selection and application design for the substrate makeup and conditions of the application location. In addition, verify the following:
 - a. Substrate Requirements for Existing or New Concrete:

- 1) Strength: 3,000 PSI minimum.
 - 2) Finish: Medium broom finish or coarser profile.
 - 3) Cure: Fifteen (15) day minimum.
 - b. Substrate Requirements for Asphalt:
 - 1) Compaction: Ninety-five (95) percent minimum.
 - 2) Finish: Rolled, compacted, smooth.
 - 3) Cure: Fifteen (15) day minimum.
 - c. Substrate Requirements for Metal:
 - 1) Surface Profile: Light sandblast or mechanical abrasion.
 - d. Substrate Requirements for Wood:
 - 1) Surface Profile: Light sandblast or mechanical abrasion.
3. Verify surface is clean and dry, and free of surface applied sealers, coloring agents, or other materials detrimental to surface bond.
4. Verify surface temperature is between 35 degrees F and 88 degrees F.
5. Verify moisture content of concrete substrate does not exceed six (6) percent.

3.02 PREPARATION

- A. Protection of In-Place Conditions: Applicator to protect applied work areas required by the Owner until work is complete to maintain product performance, design criteria and warranty.
- B. Surface Preparation: Prepare surfaces to receive work in accordance with manufacturer's instructions.
 1. Grind clean or abrade to remove surface applied sealers, coloring agents, oils, bond breakers, or any surface applied or infused materials that will cause rejection of adhesion and provide required surface profile.
 - a. Concrete Substrates:
 - 1) Grind new concrete to ensure no seal-coating has been applied.
 - 2) Grind with walk-behind or handheld grinder to CSP 3 - 5.
 - b. Asphalt Substrates:
 - 1) If seal-coated, grind to remove sealer with walk-behind or handheld grinder to CSP 3 - 5.
 2. Fill large holes or crevices resulting from the grinding process with manufacturer's recommended materials.
 3. Broom or air sweep clean surfaces free of dust and debris, vegetation and material impacting adhesion, prior to installation of liquid-polymer extrusion materials.
 4. Mask Work area.
- C. Removal of Existing Materials at Application Surface:
 1. Refer to 02 41 19 - Selective Demolition for additional requirements.

3.03 APPLICATION OF NON-SKID COATING COMPONENTS

- A. Grind substrate to CSP required as determined by substrate mix and current profile condition.
 1. Do not create divots in existing asphalt surfaces
 2. Existing asphalt with seal coat requires removal of coating prior to Non-Skid Coating application.
- B. Apply in accordance with manufacturer's written instructions. Refer to manufacturer's instructions and details.
 1. Liquid polymer extrusion material to be mixed evenly and thoroughly for two minutes minimum.
 2. Addition of catalyst and proprietary components to polymer mixture is determined by certified applicator based on current ambient weather conditions and according to viscosity.
 - a. Estimated Percentage of Sand/Catalyst for Non-Skid Coating: 20 percent.
 3. Reducer / SkidGuard Base Coat:
 - a. Reducer is not required for Non-Skid Coating installed on asphalt.
 - b. Fill surface deformities with manufacturer's recommended materials.

- c. If on Concrete; Catalyze Reducer and Seal surface. Cross roll at 90 degrees to ensure appropriate coverage and penetration.
 - d. Immediately pull tape. Wait minimum 30 minutes for Reducer or SkidGuard mix component to cure.
- 4. SkidGuard (Non-Skid Coating):
 - a. Snap chalklines or layout templates as guides in accordance with contract documents and dimensional allowances. Tape edges as needed to avoid overspray or bleed.
 - b. Mix and catalyze base component in approved color(s) in accordance with application instructions.
 - c. Pour catalyzed Base component onto mats in coverage rates indicated by manufacturer.
 - d. Apply material per manufacturers recommended procedures to ensure adequate coverage and penetration of all apertures.
 - e. Remove excess material.
 - f. Remove tape immediately in accordance with manufacturer's instructions.
 - g. Wait minimum 30 minutes for final component to cure.
 - h. When material is tack free, surface is ready for pedestrian traffic.

3.04 CLEANING

- A. Dispose of all waste material in compliance with project's Waste Management Plan in accordance with 01 74 19 - Construction Waste Management and Disposal.

3.05 PROTECTION

- A. Protect applied product from subsequent construction operation until cured or as required.
- B. Do not permit traffic over unprotected floor surface during cure.

END OF SECTION